

## Index

Cross Reference List (chemistry only)	4
Abradables	8
Aluminum Oxide	8
Chrome Carbide	10
Chrome Oxide	11
Cobalt Based Alloys	12
Copper Based Alloys	14
Iron Based Alloys	15
Molybdenum Based Alloys	16
Nickel Based Alloys	16
Nickel S/F Alloys	19
Titanium	21
Titanium Oxide	22
Tungsten Carbide	23
Yttrium Oxide	26
Zirconium Oxide	26

## Powders

<b>CROSS REFERENCE LIST (chemistry only)</b>						
<b>Powder Type</b>	<b>FST p/n</b>	<b>Metco</b>	<b>Praxair</b>	<b>Amperit</b>	<b>PAC</b>	<b>Page Nr.</b>
<b>Abradables</b>						8
AlSi-Polyester	<b>M-111</b>	601	AL 228 AL 229	–	905-3	8
ZrO <sub>2</sub> -Y <sub>2</sub> O <sub>3</sub> -Poly-hBN	<b>M-113</b>	2395	–	–	–	8
ZrO <sub>2</sub> -Y <sub>2</sub> O <sub>3</sub> -Poly	<b>M-114</b>	2460	–	–	–	8
Ni Graphite 75/25	<b>M-390</b>	307	–	–	–	8
<b>Aluminum Oxide</b>						8
Al <sub>2</sub> O <sub>3</sub>	<b>C-506/507</b>	105 6103	ALO 101 ALO 114	740	705	8
Al <sub>2</sub> O <sub>3</sub> -TiO <sub>2</sub> 97/3	<b>C-328</b>	101 6203	ALO 105 ALO 159	742	701	8
Al <sub>2</sub> O <sub>3</sub> -TiO <sub>2</sub> 87/13	<b>C-338</b>	130 6221	ALO 187 ALO 188	744	730	9
Al <sub>2</sub> O <sub>3</sub> -TiO <sub>2</sub> 87/13	<b>C-339</b>	130 6221	ALO 187 ALO 188	744	730	9
Al <sub>2</sub> O <sub>3</sub> -TiO <sub>2</sub> 60/40	<b>C-342</b>	131	ALO 121	745	731	9
Al <sub>2</sub> O <sub>3</sub> -MgO 74/26	<b>C-351</b>	–	–	–	–	10
<b>Chrome Carbide</b>						10
CrC-NiCr 80/20	<b>K-804</b>	7101 7107 7102 7103 7105	–	578	-	10
CrC-NiCr 75/25	<b>K-854</b>	7201 7202 7203 7205	1375 CRC 300	588 584	-	10
CrC-CoNiCrAlY	<b>K-880</b>	–	–	594	-	10
<b>Chrome Oxide</b>						11
Cr <sub>2</sub> O <sub>3</sub>	<b>C-604/607</b>	106 6156	Metco 6445 6155, 6156, 6416 Amdry 6415 ,6420	704 707	1106	11
Cr <sub>2</sub> O <sub>3</sub> /SiO <sub>2</sub> /TiO <sub>2</sub>	<b>C-650</b>	136 6462	CRO 192	716	732	11
Cr <sub>2</sub> O <sub>3</sub> TiO <sub>2</sub> 97/3	<b>C-667</b>	–	–	–	–	11
Cr <sub>2</sub> O <sub>3</sub> TiO <sub>2</sub> 75/25	<b>C-670</b>	6485	–	712	-	12
Cr <sub>2</sub> O <sub>3</sub> TiO <sub>2</sub> 60/40	<b>C-677</b>	6483	–	–	–	12
<b>Cobalt Based Alloys</b>						12

<b>CROSS REFERENCE LIST (chemistry only)</b>						
<b>Powder Type</b>	<b>FST p/n</b>	<b>Metco</b>	<b>Praxair</b>	<b>Amperit</b>	<b>PAC</b>	<b>Page Nr.</b>
T-800	<b>M-499</b>	68 3001 4800	CO 111 1248	342	T800	12
T-400	<b>M-494</b>	66 3002	CO 109 1247	340	T400	12
Alloy 12	<b>M-481</b>	8102	–	–	–	13
Alloy 6	<b>M-484</b>	4060 8101	CO 106 1256	344	6 46	13
Alloy 1	<b>M-487</b>	8100	–	–	–	13
<b>Copper Based Alloys</b>						14
Pure Copper	<b>M-901</b> <b>M-901P</b>	55 1007	CU 105 CU 159	–	10	14
CuAlFe (Al-Bronze)	<b>M-950</b>	51 1004	CU 114 CU 104	–	16	14
CuAl (Al-Bronze)	<b>M-952</b>	–	–	–	–	14
<b>Iron Based Alloys</b>						15
316L Stainless	<b>M-684</b>	41 1003	FE 101 1236	377	96	15
431 Stainless	<b>M-687</b>	42	–	–	97	15
420 Stainless	<b>M-642</b>	1002	–	–	–	15
Ultra Hard Steel	<b>M-688</b>	–	–	–	–	15
<b>Molybdenum Based Alloys</b>						16
Mo	<b>M-801</b>	63 4063	MO 102 MO 103 1293	105 106 109	118	16
Mo-25NiS/F	<b>M-855</b>	1371	–	–	902	16
MB NiCr	<b>M-880</b>	–	–	–	–	16
<b>Nickel Based Alloys</b>						16
Pure Ni	<b>M-300</b>	56	NI 101 NI 118 1166	175	900	16
NiCr 80/20	<b>M-301</b>	43 5640 4535	NI 105 NI 106 NI 107 1262	250 251	98	17
NiAl 95/5	<b>M-358</b>	480	NI 185 Ni 970	280 281	906	17
Alloy 625	<b>M-325</b>	1005	NI 328 1265	380	625	17

## Powders

<b>CROSS REFERENCE LIST (chemistry only)</b>						
<b>Powder Type</b>	<b>FST p/n</b>	<b>Metco</b>	<b>Praxair</b>	<b>Amperit</b>	<b>PAC</b>	<b>Page Nr.</b>
Alloy 718	<b>M-328</b>	1006	NI 202 1278	407	718	17
Alloy C-276	<b>M-341</b>	4276	NI 544 1269	409	C276	18
Alloy C-22	<b>M-342</b>	–	–	–	–	18
Alloy X	<b>M-344</b>	–	–	–	–	18
<b>Nickel S/F Alloys</b>						19
NiCrSiB (59-64 HRC)	<b>M-771</b>	15 2001	–	–	–	19
NiCrSiB (50-55 HRC)	<b>M-770</b>	14	–	–	–	19
NiCrSiB (35-40 HRC)	<b>M-772</b>	12	–	–	–	19
NiCrSiBCuMo (58-64 HRC)	<b>M-778</b>	16	–	–	–	20
NiCrSiB (30-35 HRC)	<b>M-774</b>	–	–	–	–	19
NiCrSiB (35-43 HRC)	<b>M-775</b>	–	–	–	–	19
NiCrSiB (45-50 HRC)	<b>M-776</b>					20
NiCrSiB (55-60 HRC)	<b>M-773</b>					19
NiCrSiBW (55-58 HRC)	<b>M-781</b>					20
NiCrSiBW (57-61 HRC)	<b>M-782</b>					20
NiCr/SF WC	<b>M-733</b>					20
NiCr/SF WC-Co	<b>M-735</b>	31C				21
NiCr/SF WC	<b>M-737</b>					21
<b>Titanium</b>						21
Pure Ti	<b>M-222</b>	4010	-	155	-	21
Ti 6Al 4V	<b>M-223</b>					21
Pure Ti	<b>M-224</b>					22
Ti 6Al 4V	<b>M-225</b>					22
<b>Titanium Oxide</b>						22
TiO <sub>2</sub>	<b>C-408</b>	102	-	782	702	22
<b>Tungsten Carbide</b>						23
WC-Co 88/12	<b>K-624</b>	3101 3106 3102 3103 5105	1342 WC 727	518	125 126 127	23

<b>CROSS REFERENCE LIST (chemistry only)</b>						
<b>Powder Type</b>	<b>FST p/n</b>	<b>Metco</b>	<b>Praxair</b>	<b>Amperit</b>	<b>PAC</b>	<b>Page Nr.</b>
WC-Co 83/17	<b>K-674</b>	3201 3202 3203 5143	1343 WC 729	526	200	24
WC-Co-Cr 86/10/4	<b>K-647</b> <b>K-648</b>	5847 3652 3653 3655 3654	1350 WC 731	558 557	–	24
WC-Co-Cr 86/10/4	<b>K-646</b>	5843 3903	WC 496	554	–	24
WC-Ni 88/12	<b>K-611</b>	330...	1310 WC 791	547	–	23
WC-Ni 83/17	<b>K-612</b>	3501 3502 3503 3505	1310 WC 724	547	–	23
WC-CoCrNi 85/9/5/1	<b>K-665</b>	3601 3602 3603 3604				25
WC-CrC-Ni 73/20/7	<b>K-607</b>	3701 3707 3702-1 3703	1356 WC 733	551		26
<b>Yttrium Oxide</b>						26
Y2O3	<b>C-200</b>	6035 6015	YO 118 YO 125	849	2100	26
<b>Zirconium Oxide</b>						26
ZrO <sub>2</sub> -Y <sub>2</sub> O <sub>3</sub>	<b>C-297</b>			825		26
ZrO <sub>2</sub> -Y <sub>2</sub> O <sub>3</sub>	<b>C-295</b>	204 231 234	ZRO 182 AI 1075 1484	827 831 832	2008	27
ZrO <sub>2</sub> -22MgO	<b>C-234</b>	210	ZRO 103		810	27
ZrO <sub>2</sub> -5CaO	<b>C-241</b>	201				27

## Powders

ABRADABLES				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
AlSi-Polyester	Si 12.0% Polyester 40.0% Al Bal.  Blend	<b>M-111.92</b>	-125 +12 $\mu\text{m}$	<ul style="list-style-type: none"> <li>• Plasma.</li> <li>• Premium Silicon Aluminum and Polyester powder.</li> <li>• Quality abradable coatings for clearance control coatings in aircraft engines.</li> <li>• Application can also be found in turbo charges and land based turbines.</li> <li>• Useful up to 325°C (620°F).</li> </ul>
ZrO <sub>2</sub> Y <sub>2</sub> O <sub>3</sub> Polyester	ZrO <sub>2</sub> Bal. Y <sub>2</sub> O <sub>3</sub> 7,5% Polyester 4.0%  Blend	<b>M-114.985</b>	-180 +10 $\mu\text{m}$  Average: 70 $\mu\text{m}$	<ul style="list-style-type: none"> <li>• Coatings of these materials can be applied with high porosity levels.</li> <li>• Sprayable to higher levels than normal Zirconia Coatings.</li> </ul>
ZrO <sub>2</sub> Y <sub>2</sub> O <sub>3</sub> Polyester hBN	ZrO <sub>2</sub> Bal. Y <sub>2</sub> O <sub>3</sub> 7,5% Polyester 4.5% hBN 0.7%  Blend	<b>M-113.985</b>	-180 +10 $\mu\text{m}$  Average: 70 $\mu\text{m}$	<ul style="list-style-type: none"> <li>• Coatings of these materials can be applied with high porosity levels.</li> <li>• Sprayable to higher levels than normal Zirconia Coatings.</li> </ul>
Ni Graphite 75/25	Ni Bal. C 25.0%	<b>M-390.91</b>	-106 +45 $\mu\text{m}$	<ul style="list-style-type: none"> <li>• Coating service temperature capability approaching 480 °C.</li> <li>• Suitable for abradable coatings to rub against nickel alloy and steel.</li> <li>• Used in the glass industry as an low friction protective coating.</li> </ul>

ALUMINUM OXIDE				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
Al <sub>2</sub> O <sub>3</sub>	Al <sub>2</sub> O <sub>3</sub> > 99.5%	<b>C-506.01</b>	-25 +5 $\mu\text{m}$	<ul style="list-style-type: none"> <li>• Good for abrasion, erosion and sliding wear applications</li> <li>• Good in alkalis and acid environments</li> <li>• Excellent dielectric properties</li> <li>• Useful up to 1600°C (3000°F)</li> <li>• Grind only with silicon carbide or diamond wheels.</li> </ul>
	Fused & Crushed	<b>C-506.21</b>	-45 +5 $\mu\text{m}$	
		<b>C-506.25</b>	-45 +22 $\mu\text{m}$	

<b>ALUMINUM OXIDE</b>				
<b>Powder Type</b>	<b>Nom.Composition</b>	<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>
Al <sub>2</sub> O <sub>3</sub>	Al <sub>2</sub> O <sub>3</sub> > 99.9%  Spheridized	C-507.02	-20 +5 µm	<ul style="list-style-type: none"> <li>• High Purity Aluminium Oxide.</li> <li>• Good for abrasion, erosion and sliding wear applications.</li> <li>• Good in alkalis and acid environments.</li> <li>• Excellent dielectric properties.</li> <li>• Useful up to 1600°C (3000°F).</li> <li>• Grind only with silicon carbide or diamond wheels.</li> </ul>
		C-507.17	-38 +10 µm	
		C-507.23	-45 +15 µm	
		C-507.32	-53 +15 µm	
Al <sub>2</sub> O <sub>3</sub> -TiO <sub>2</sub> 97/3	Al <sub>2</sub> O <sub>3</sub> 97.0% TiO <sub>2</sub> 3.0%  Fused & Crushed	C-328.01	-25 +5 µm	<ul style="list-style-type: none"> <li>• Coatings are recommended for resistance to wear by abrasive grains, hard surfaces, fiber and thread, fretting, cavitation and particle erosion.</li> <li>• Resistance top cavitation, and to the effects of molten zinc, aluminium and copper.</li> <li>• Useful in the textile industry on any machine element application which comes in contact with fibers and threads.</li> </ul>
		C-328.25	-45 +22 µm	
Al <sub>2</sub> O <sub>3</sub> -TiO <sub>2</sub> 87/13	Al <sub>2</sub> O <sub>3</sub> 87.0% TiO <sub>2</sub> 13.0%  Fused & Crushed	C-338.01	-25 +5 µm	<ul style="list-style-type: none"> <li>• Similar to C-328, but less hard and less brittle</li> </ul>
		C-338.25	-45 +22 µm	
Al <sub>2</sub> O <sub>3</sub> -TiO <sub>2</sub> 87/13	Al <sub>2</sub> O <sub>3</sub> 87.0% TiO <sub>2</sub> 13.0%  Blend	C-339.01	-25 +5 µm	<ul style="list-style-type: none"> <li>• Similar to C-338</li> <li>• Different morphology</li> </ul>
		C-339.25	-45 +22 µm	
Al <sub>2</sub> O <sub>3</sub> -TiO <sub>2</sub> 60/40	Al <sub>2</sub> O <sub>3</sub> 60.0% TiO <sub>2</sub> 40.0%  Fused & Crushed	C-342.01	-22 +5 µm	<ul style="list-style-type: none"> <li>• Chemical processing industry to resist weak acidic environments</li> <li>• Textile manufacturing equipment and tooling</li> <li>• Pump components, shaft sleeves and mechanical seals used in a variety of industries.</li> </ul>
		C-342.25	-45 +22 µm	

## Powders

ALUMINUM OXIDE				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
Al <sub>2</sub> O <sub>3</sub> -MgO 74/26	Al <sub>2</sub> O <sub>3</sub> 74.0%	<b>C-351.45</b>	-63 +10 µm	<ul style="list-style-type: none"> <li>• Spinel</li> <li>• High thermal shock resistance.</li> <li>• Because of resistance to wetting by molten aluminium many applications in the aluminium industry can be found.</li> </ul> Commonly used for the coating of oxygen sensors for gas erosion resistance and gas permeability control.
	MgO 26.0%		-75 +20 µm	
	HOSP			

CHROME CARBIDE				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
CrC-NiCr 80/20	NiCr 20.0%	<b>K-804.17</b>	-38 +10 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Useful up to 870°C (1600°F)</li> <li>• Higher hardness than K-854.23</li> <li>• Good corrosion, abrasion, particle erosion, fretting and cavitation resistance</li> <li>• Good hot gas corrosion resistance</li> <li>• Excellent for high temperature wear applications</li> <li>• Best finished by wet grinding.</li> </ul>
	CrC Bal.		-45 +15 µm	
	Agglomerated & Sintered	<b>K-804.23</b>		
WC-CrC-NiCrCo 45/37/18	W Bal.	<b>K-810.17</b>	-38+10 µm	<ul style="list-style-type: none"> <li>• HVOF</li> <li>• Usefull up to 700 C</li> <li>• Dense, oxidation and erosion resistant coatings</li> <li>• Good hot gas corrosion resistance</li> <li>• Cost efficient due to lower density then WC based materials</li> </ul>
	Cr 41.0%			
	Ni 11,5%			
	Co 7.0%			
	C 8.0%			
	Agglomerated & Sintered			
CrC-NiCr 75/25	NiCr 25.0%	<b>K-854.17</b>	-38 +10 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Useful up to 870°C (1600°F)</li> <li>• Good corrosion, abrasion, particle erosion, fretting and cavitation resistance</li> <li>• Good hot gas corrosion resistance</li> <li>• Excellent for high temperature wear applications</li> <li>• Higher DE than K-804.22</li> <li>• Best finished by wet grinding.</li> </ul>
	CrC Bal.		-45 +15 µm	
	Agglomerated & Sintered	<b>K-854.23</b>		

<b>CHROME CARBIDE</b>					
<b>Powder Type</b>	<b>Nom.Composition</b>	<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>	
CrC-CoNiCrAlY 75/25	Co 9.0%	<b>K-880.17</b>	-38 +10 μm	<ul style="list-style-type: none"> <li>• HVOF</li> <li>• Useful up to 1000°C (1800°F)</li> <li>• Excellent wear and erosion resistance up to 1000°C (1800°F)</li> <li>• Better oxidation resistance than CrC-NiCr</li> <li>• Used for furnace roll in steel industry and turbine components.</li> </ul>	
	Ni 8.0%	<b>K-880.23</b>	-45 +15 μm		
Al 2.0%					
Y 0.15%					
C 9.5%					
	Cr Bal.				
	Agglomerated & Sintered				
<b>CHROME OXIDE</b>					
<b>Powder Type</b>	<b>Nom.Composition</b>	<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>	
Cr <sub>2</sub> O <sub>3</sub>	Cr <sub>2</sub> O <sub>3</sub> > 99.8%	<b>C-604.03</b>	-25 +10 μm	<ul style="list-style-type: none"> <li>• Plasma</li> <li>• Hard, dense wear resistant coating</li> <li>• Insoluble in acids, alkalis and alcohol</li> <li>• Useful up to 540°C (1000°F)</li> <li>• Excellent engraving properties</li> <li>• Used for anilox rolls, pump seal areas, wear rings etc.</li> <li>• Grind only, use silicon carbide or diamond wheels.</li> </ul>	
	Reaction Sintered	<b>C-604.151</b>	-30 +10 μm		
		<b>C-604.25</b>	-45 +22 μm		
Cr <sub>2</sub> O <sub>3</sub>	Cr <sub>2</sub> O <sub>3</sub> > 99.5%	<b>C-607.01</b>	-25 +5 μm		
	Fused & Crushed	<b>C-607.25</b>	-45 +22 μm		
Cr <sub>2</sub> O <sub>3</sub> /SiO <sub>2</sub> /TiO <sub>2</sub>	Cr <sub>2</sub> O <sub>3</sub> Bal.	<b>C-650.01</b>	-25 +5 μm		<ul style="list-style-type: none"> <li>• Similar to C-604</li> <li>• Better impact resistant than C-604</li> <li>• Good low friction features</li> <li>• Grind only, use silicon carbide or diamond wheels.</li> </ul>
	SiO <sub>2</sub> 5.0%	<b>C-650.25</b>	-45 +22 μm		
	TiO <sub>2</sub> 3.0%				
	Fused & Crushed	<b>C-650.45</b>	-63 +15 μm		
Cr <sub>2</sub> O <sub>3</sub> TiO <sub>2</sub> 97/3	Cr <sub>2</sub> O <sub>3</sub> Bal.	<b>C-667.151</b>	-30 +10 μm	<ul style="list-style-type: none"> <li>• Similar to C-604</li> <li>• Lower Hardness than C-604 but better toughness than C-604</li> <li>• Used in wear applications where more toughness is needed</li> <li>• Grind only, use silicon carbide or diamond wheels.</li> </ul>	
	TiO <sub>2</sub> 3.0%	<b>C-667.25</b>	-45 +22 μm		
	Reaction Sintered				

## Powders

CHROME OXIDE				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
Cr <sub>2</sub> O <sub>3</sub> TiO <sub>2</sub> 75/25	Cr <sub>2</sub> O <sub>3</sub> Bal. TiO <sub>2</sub> 25.0%  Reaction Sintered	C-670.151	-30 +10 μm	<ul style="list-style-type: none"> <li>• Similar to C-667</li> <li>• Lower Hardness than C-667 but better toughness than C-667</li> <li>• Used in wear applications where more toughness is needed</li> <li>• Grind only, use silicon carbide or diamond wheels.</li> </ul>
		C-670.25	-45 +22 μm	
Cr <sub>2</sub> O <sub>3</sub> TiO <sub>2</sub> 60/40	Cr <sub>2</sub> O <sub>3</sub> Bal. TiO <sub>2</sub> 40.0%  Reaction Sintered	C-677.151	-30 +10 μm	<ul style="list-style-type: none"> <li>• Similar to C-670</li> <li>• Lower Hardness than C-670 but better toughness than C-670</li> <li>• Used in wear applications where more toughness is needed</li> <li>• Grind only, use silicon carbide or diamond wheels.</li> </ul>
		C-677.25	-45 +22 μm	
COBALT BASED ALLOYS				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
T-800	Mo 28.0% Cr 17.0% Si 3.5% Co Bal.  Gas Atomized	M-499.22	-45 +10 μm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Excellent sliding wear properties from room temperature up to 810°C (1500°F)</li> <li>• Good hot hardness, oxidation and corrosion properties</li> <li>• Low coefficient of friction</li> <li>• Suitable where there is low lubrication</li> <li>• Machines readily with Silicon Carbide tools.</li> <li>• Similar to Tribaloy® 800</li> </ul>
		M-499.33	-53 +20 μm	
T-400	Mo 28.0% Cr 8.0% Si 2.5% Co Bal.  Gas Atomized	M-494.25	-45 +22 μm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Excellent wear properties from room temperature up to 810°C (1500°F)</li> <li>• Good hot hardness, oxidation and corrosion properties</li> <li>• Low coefficient of friction</li> <li>• Wet grinding with Silicon Carbide tools</li> <li>• Similar to Tribaloy® 400</li> </ul>
		M-494.33	-53 +20 μm	

<b>COBALT BASED ALLOYS</b>					
<b>Powder Type</b>	<b>Nom.Composition</b>		<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>
Alloy 12	Cr	29.0%	<b>M-481.25</b>	-45 +22 µm	<ul style="list-style-type: none"> <li>• Equivalent to Stellite® 12</li> <li>• Resistant to wear, galling and corrosion and retain these properties at high temperatures.</li> <li>• It is regarded as the industry standard for general-purpose wear resistance applications.</li> <li>• Good resistance to impact and cavitation erosion.</li> <li>• Examples include valve seats and gates; pump shafts and bearings, erosion shields and rolling couples.</li> </ul>
	W	8.0%	<b>M-481.33</b>	-53 +20 µm	
	C	1.5%	<b>M-481.71</b>	-90 +45 µm	
	Co	Bal.	<b>M-481.93</b>	-125 +45 µm	
	Gas Atomized				
Alloy 6	Cr	29.0%	<b>M-484.25</b>	-45 +22 µm	<ul style="list-style-type: none"> <li>• Equivalent to Stellite® 6</li> <li>• Resistant to wear, galling and corrosion and retain these properties at high temperatures.</li> <li>• It is regarded as the industry standard for general-purpose wear resistance applications.</li> <li>• Good resistance to impact and cavitation erosion.</li> <li>• Examples include valve seats and gates; pump shafts and bearings, erosion shields and rolling couples.</li> </ul>
	W	4.5%	<b>M-484.33</b>	-53 +20 µm	
	C	1.2%	<b>M-484.71</b>	-90 +45 µm	
	Co	Bal.	<b>M-484.93</b>	-125 +45 µm	
	Gas Atomized				
Alloy 1	Cr	29,0%	<b>M-487.25</b>	-45 +22 µm	<ul style="list-style-type: none"> <li>• Equivalent to Stellite® 1</li> <li>• Resistant to wear, galling and corrosion and retain these properties at high temperatures.</li> <li>• It is regarded as the industry standard for general-purpose wear resistance applications.</li> <li>• Good resistance to impact and cavitation erosion.</li> <li>• Examples include valve seats and gates; pump shafts and bearings, erosion shields and rolling couples.</li> </ul>
	W	13.0%	<b>M-487.33</b>	-53 +20 µm	
	C	2.5%	<b>M-487.71</b>	-90 +45 µm	
	Co	Bal	<b>M-487.93</b>	-125 +45 µm	
	Gas Atomized				

*Tribaloy is a registered trade mark of Kennametal Stellite, Inc.  
Stellite is a registered trade mark of Kennametal Stellite, Inc.*

## Powders

COPPER BASED ALLOYS				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
Pure Copper	Cu Gas Atomized P=High Purity	<b>M-901.17</b>	-38 +10 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma, Cold Gas</li> <li>• Good electrical and thermal conductivity</li> <li>• Non Magnetic</li> <li>• Used for build-up and repair of copper based alloys</li> <li>• Applications can be found in printing industry. Resistance against corrosive effects of inks</li> <li>• Dense coatings</li> <li>• Machine with high speed steel or carbide tools.</li> </ul>
		<b>M-901P.17</b>	-38 +10 µm	
		<b>M-901.25</b>	-45 +22 µm	
		<b>M-901P.25</b>	-45 +22 µm	
		<b>M-901.33</b>	-53 +20 µm	
		<b>M-901.71</b>	-90 +45 µm	
Al-Bronze	Al            9.5% Fe            1.0% Cu            Bal. Gas Atomized	<b>M-950.33</b>	-53 +20 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Good bearing material</li> <li>• Resistant to fretting and galling at low temperatures</li> <li>• Easily machined coatings</li> <li>• Typical applications include: pump parts, piston guides, seal area's (soft bearing surfaces)</li> <li>• Good cavitation resistance</li> <li>• Machines with high speed steel or carbide tools.</li> </ul>
		<b>M-950.71</b>	-90 +45 µm	
Al-Bronze	Al            10.0% Cu            Bal. Gas Atomized	<b>M-952.33</b>	-53 +20 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Good bearing material</li> <li>• Resistant to fretting and galling at low temperatures</li> <li>• Easily machined coatings</li> <li>• Typical applications include: pump parts, piston guides, seal area's (soft bearing surfaces)</li> <li>• Good cavitation resistance</li> <li>• Machines with high speed steel or carbide tools.</li> </ul>
		<b>M-952.71</b>	-90 +45 µm	

IRON BASED ALLOYS				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
316L Stainless	Cr 17.00%	<b>M-684.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Good corrosion properties</li> <li>• Smooth and easy to machine coatings</li> <li>• Good against fretting, cavitation and erosion</li> <li>• Good for dimensional restoration and build-up</li> <li>• Easily machined with carbide or tool steel.</li> </ul>
	Ni 12.00%	<b>M-684.33</b>	-53 +20 µm	
	Mo 2.5%	<b>M-684.71</b>	-90 +45 µm	
	Si <0.75%			
	C <0.03%			
	Fe Bal.			
	Gas Atomized			
431 Stainless	Cr 16.0%	<b>M-687.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Corrosion resistant coating used mostly for repair and wear applications, requiring a hard ground finish</li> <li>• The coating may contain martensitic phases</li> <li>• Easily machined with carbide or tool steel.</li> </ul>
	Ni 2.0%	<b>M-687.33</b>	-53 +20 µm	
	C 0.03%	<b>M-687.71</b>	-90 +45 µm	
	Fe Bal.			
	Gas Atomized			
420 Stainless	Cr 13.00%	<b>M-642.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Martensitic Stainless Steel</li> <li>• Repair and Wear resistance Application</li> </ul>
	C 0.08%	<b>M-642.33</b>	-53 +20 µm	
	Fe Bal.	<b>M-642.71</b>	-90 +45 µm	
	Gas Atomized			
Ultra Hard Steel	Cr 32.0%	<b>M-688.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Hard bearing surfaces: bearing journals, fuel pump rotors, sleeves</li> <li>• Resist abrasive grains: cylinder liners, pistons, pump plungers, hydraulic rams, crankshaft bearings</li> <li>• Resist fretting (intended or non-intended motion): machine bedways, wear rings, press fits, bearing seats</li> <li>• Resist particle erosion (low temperature): exhaust fans, hydroelectric valves</li> <li>• Salvage and buildup on grindable steel: mis-machine parts, worn parts</li> <li>• High temperature environments to resist oxidation</li> </ul>
	Ni 8.0%	<b>M-688.33</b>	-53 +20 µm	
	B 4.1%			
	C 0.6%			
	Gas Atomized			

## Powders

MOLYBDENUM BASED ALLOYS				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
Mo	Mo >99.0%	<b>M-801.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Plasma</li> <li>• Tough coatings with fair hardness and excellent sliding properties.</li> <li>• Useful up to 320°C</li> <li>• Fret resistant</li> <li>• Bonds well to steel</li> <li>• Used for pump parts, piston rings, synchronizing rings, press fits, valves, gears and other similar applications.</li> </ul>
	Agglomerated & Sintered	<b>M-801.52</b>	-75 +25 µm	
		<b>M-801.71</b>	-90 +45 µm	
Mo-25NiS/F	Mo 75.0% NiCrSiB 25.0%  Blend	<b>M-855.691</b>	-90 +15 µm	<ul style="list-style-type: none"> <li>• Plasma</li> <li>• Useful up to 350°C</li> <li>• Low coefficient of friction</li> <li>• Wear resistant coating with excellent sliding properties</li> <li>• Bonds well to steel</li> <li>• Used for pump parts, piston rings, synchronizing rings, press fits, valves</li> <li>• Can be finished by wet grinding.</li> </ul>
MoB-NiCr	Mo Bal. B 7.5% Ni 20% Cr 5%	<b>M-880.25</b>	-45 +22 µm	<ul style="list-style-type: none"> <li>• Resistant to high temperature erosion and sliding wear</li> <li>• Thermal shock resistance is fair</li> <li>• High temperature corrosion is good</li> <li>• Excellent non-stick properties</li> <li>• Excellent resistance to molten metals such and Aluminum and Zinc</li> </ul>

NICKEL BASED ALLOYS				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
Pure Ni	Ni >99.8%	<b>M-300.25</b>	-45 +25 µm	<ul style="list-style-type: none"> <li>• Plasma, HVOF</li> <li>• Can be used for salvage and build-up of Nickel based alloys that have been damaged or mis-machined</li> <li>• Easily machined</li> <li>• Coatings with dense and moderate hardness</li> <li>• Machines with most grades of cutting tools.</li> </ul>
	Gas Atomized	<b>M-300.71</b>	-90 +45 µm	

<b>NICKEL BASED ALLOYS</b>				
<b>Powder Type</b>	<b>Nom.Composition</b>	<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>
NiCr 80/20	Cr 20.0%	<b>M-301.25</b>	-45 +22 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Good to resist oxidation and corrosion gases up to 980°C (1800°F)</li> <li>• Good for general repair and build-up</li> <li>• Suitable as ceramic bondcoat</li> <li>• Good bonding</li> <li>• Easily machined with all grades of cutting tools.</li> </ul>
	Ni Bal.	<b>M-301.33</b>	-53 +20 µm	
	Gas Atomized	<b>M-301.71</b>	-90 +45 µm	
NiAl 95/5	Al 5.0%	<b>M-358.33</b>	-53 +20 µm	<ul style="list-style-type: none"> <li>• Plasma</li> <li>• Self bonding to most metallic surfaces</li> <li>• Good oxidation and abrasion resistant</li> <li>• Recommended for use as oxidation resistant bond coats which can be used below 800°C (1470°F)</li> <li>• Good for general repair and build-up</li> <li>• Thick coatings are possible.</li> </ul>
	Ni 95.0%	<b>M-358.71</b>	-90 +45 µm	
Alloy 625	Cr 21.0%	<b>M-325.25</b>	-45 +22 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Excellent high temperature oxidation and corrosion properties</li> <li>• Good for repair and build-up of similar chemistry super alloy components</li> <li>• Useful up to 980°C (1800°F)</li> <li>• Machines ready with Silicon-Carbide tools.</li> <li>• Similar to Inconel® 625</li> </ul>
	Mo 9.0%	<b>M-325.33</b>	-53 +20 µm	
	Nb 3.7%	<b>M-325.71</b>	-90 +45 µm	
Alloy 718	Ni Bal.			<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Excellent high temperature oxidation and corrosion properties</li> <li>• Good for repair and build-up of similar chemistry super alloy components</li> <li>• Useful up to: 980°C (1800°F)</li> <li>• Machines ready with Silicon-Carbide tools.</li> <li>• Similar to Inconel® 718</li> </ul>
	Cr 19.0%	<b>M-328.25</b>	-45 +22 µm	
	Fe 18.0%	<b>M-328.33</b>	-53 +20 µm	
	Mo 3.0%	<b>M-328.71</b>	-90 +45 µm	
	Nb+Ta 5.0%			
Ti 1.0%				
Ni Bal.				
	Gas Atomized			

## Powders

NICKEL BASED ALLOYS				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
Alloy C-276	Cr 15.5%	<b>M-341.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Excellent high temperature oxidation and corrosion properties</li> <li>• Good for repair and build-up of similar chemistry super alloy components.</li> <li>• Equivalent to Hastelloy C276</li> </ul>
	Mo 16.0%	<b>M-341.33</b>	-53 +20 µm	
Alloy C-22	W 4.0%	<b>M-342.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Excellent high temperature oxidation and corrosion properties</li> <li>• Good for repair and build-up of similar chemistry super alloy components.</li> <li>• Equivalent to Hastelloy C22</li> </ul>
	Fe 4.0%			
Alloy X	Ni Bal.	<b>M-344.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• HVOF, Plasma</li> <li>• Excellent high temperature oxidation and corrosion properties</li> <li>• Good for repair and build-up of similar chemistry super alloy components.</li> <li>• Equivalent to Hastelloy X</li> </ul>
	Gas Atomized			

<b>NICKEL S/F ALLOYS</b>					
<b>Powder Type</b>	<b>Nom.Composition</b>		<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>
NiCrSiB (50-55HRC)	Ni	Bal.	<b>M-770.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	Cr	12.0%	<b>M-770.33</b>	-53 +20 µm	
	B	3.0%	<b>M-770.91</b>	-106 +45 µm	
	Si	4.0%			
	C	0.6%			
	Fe	3.75%			
NiCrSiB (59-64HRC)	Ni	Bal.	<b>M-771.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	Cr	17.0%	<b>M-771.33</b>	-53 +20 µm	
	B	3.3%	<b>M-771.91</b>	-106 +45 µm	
	Si	4.3%			
	C	0.9%			
	Fe	4.0%			
NiCrSiB (35-40HRC)	Ni	Bal.	<b>M-772.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	Cr	8.0%	<b>M-772.33</b>	-53 +20 µm	
	B	1.9%	<b>M-772.91</b>	-106 +45 µm	
	Si	3.1%			
	C	0.5%			
	Fe	2.5%			
NiCrSiB (55-60HRC)	Ni	Bal.	<b>M-773.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	Cr	15.0%	<b>M-773.33</b>	-53 +20 µm	
	B	3.0%	<b>M-773.91</b>	-106 +45 µm	
	Si	4.6%			
	C	0.7%			
	Fe	4.5%			
NiCrSiB (30-35HRC)	Ni	Bal.	<b>M-774.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	Cr	6.3%	<b>M-774.33</b>	-53 +20 µm	
	B	1.2%	<b>M-774.91</b>	-106 +45 µm	
	Si	4.0%			
	C	0.4%			
	Fe	1.75%			
NiCrSiB (35-43HRC)	Ni	Bal.	<b>M-775.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	Cr	10.0%	<b>M-775.33</b>	-53 +20 µm	
	B	1.8%	<b>M-775.91</b>	-106 +45 µm	
	Si	3.2%			
	C	0.45%			
	Fe	2.5%			

## Powders

NICKEL S/F ALLOYS					
Powder Type	Nom.Composition		FST p/n	Size Range	Typical Properties and Applications
NiCrSiB (45-50HRC)	Cr	13.0%	<b>M-776.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	B	2.5%	<b>M-776.33</b>	-53 +20 µm	
	Si	3.4%			
	C	0.45%			
	Fe	4.5%	<b>M-776.91</b>	-106 +45 µm	
NiCrSiB (58-64HRC)	Ni	Bal.	<b>M-778.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	Cr	17.0%			
	B	3.8%	<b>M-778.33</b>	-53 +20 µm	
	Si	4.0%			
	C	0.6%	<b>M-778.91</b>	-106 +45 µm	
	Fe	3.0%			
	Cu	2.5%			
Mo	3,3%				
NiCrSiB (55-58HRC)	Ni	Bal.	<b>M-781.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	Cr	13.7%			
	B	2.6%	<b>M-781.33</b>	-53 +20 µm	
	Si	3.7%			
	C	0.6%	<b>M-781.91</b>	-106 +45 µm	
	Fe	3.5%			
W	15.0%				
NiCrSiB (57-61HRC)	Ni	Bal.	<b>M-782.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• Self Fluxing type alloy</li> <li>• Excellent corrosion and wear resistance</li> <li>• Serviceable up to 820°C (1500°F)</li> <li>• Coatings are dense and essentially oxide free</li> <li>• Machine with carbide tools or grind.</li> </ul>
	Cr	12.5%			
	B	3.0%	<b>M-782.33</b>	-53 +20 µm	
	Si	3.0%			
	C	0.5%	<b>M-782.91</b>	-106 +45 µm	
	Fe	3.8%			
W	12.5%				
NiCr-SF + WC	WC (CTC)	35%	<b>M-733.91</b>	-106 +45 µm	<ul style="list-style-type: none"> <li>• Blend with Fused Tungsten Carbide</li> <li>• Coatings are extremely wear resistant to abrasive grains, hard surfaces, fretting and particle erosion.</li> <li>• The most wear resistant of all self fluxing coatings</li> <li>• Essentially Cobalt free for stain resistance.</li> </ul>
	NiCr-S/F (60Rc)	65%			
	Blend				

<b>NICKEL S/F ALLOYS</b>				
<b>Powder Type</b>	<b>Nom.Composition</b>	<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>
NiCr-SF + WC-Co	WC-Co (A/S) 35% NiCr-S/F 65% (60Rc)  Blend	<b>M-735.93</b>	-125 +45 µm	<ul style="list-style-type: none"> <li>• Blend with Agglomerated WC-Co Tungsten Carbide</li> <li>• Coatings are extremely wear resistant to abrasive grains, hard surfaces, fretting and particle erosion.</li> <li>• The most wear resistant of all self fluxing coatings</li> <li>• Essentially Cobalt free for stain resistance.</li> </ul>
NiCr-SF + WC	WC (CTC) 35% NiCr-S/F 65% (50Rc)  Blend	<b>M-737.91</b>	-106 +45 µm	<ul style="list-style-type: none"> <li>• Blend with Fused Tungsten Carbide</li> <li>• Coatings are extremely wear resistant to abrasive grains, hard surfaces, fretting and particle erosion.</li> <li>• The most wear resistant of all self fluxing coatings</li> <li>• Essentially Cobalt free for stain resistance.</li> </ul>

<b>TITANIUM</b>				
<b>Powder Type</b>	<b>Nom.Composition</b>	<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>
Pure Ti	Ti  HDH CP (Blocky)	<b>M-222.91</b>	-106 +45 µm	<ul style="list-style-type: none"> <li>• In accordance with ASTM F1580-12</li> <li>• VPS, LPPS</li> <li>• Good corrosion resistance against salt water, Cl containing solutions and oxidizing acid solutions</li> <li>• Material for biomedical applications.</li> </ul>
		<b>M-222.995</b>	-180 +75 µm	
Pure Ti 6Al 4V	Al 6.0% V 4.0% Ti Bal.  HDH CP (Blocky)	<b>M-223.91</b>	-106 +45 µm	<ul style="list-style-type: none"> <li>• In accordance with ASTM F1580-12</li> <li>• VPS, LPPS</li> <li>• Good corrosion resistance against salt water, Cl containing solutions and oxidizing acid solutions</li> <li>• Material for biomedical applications.</li> </ul>
		<b>M-223.995</b>	-180 +75 µm	

## Powders

Pure Ti	Ti PREP (Spherical)	<b>M-224.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• In accordance with ASTM F1580-12</li> <li>• VPS, LPPS</li> <li>• Good corrosion resistance against salt water, Cl containing solutions and oxidizing acid solutions</li> <li>• Material for biomedical applications.</li> </ul>
		<b>M-224.91</b>	-106 +45 µm	
Pure Ti 6Al 4V	Al        6.0% V         4.0% Ti        Bal.  PREP (Spherical)	<b>M-225.23</b>	-45 +15 µm	<ul style="list-style-type: none"> <li>• In accordance with ASTM F1580-12</li> <li>• VPS, LPPS</li> <li>• Good corrosion resistance against salt water, Cl containing solutions and oxidizing acid solutions</li> <li>• Material for biomedical applications.</li> </ul>
		<b>M-225.91</b>	-106 +45 µm	

TITANIUM OXIDE				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
TiO <sub>2</sub>	TiO <sub>2</sub> > 99.5%  Fused & Crushed	<b>C-408.01</b>	-25 +5 µm	<ul style="list-style-type: none"> <li>• Moderate abrasive wear resistance</li> <li>• Lower hardness than Al<sub>2</sub>O<sub>3</sub>-TiO<sub>2</sub> coatings</li> <li>• Decorative "black" coatings</li> <li>• Slightly conductive; Static electricity does not build-up on coating surface</li> <li>• Soluble in alkalis and sulfuric acid</li> <li>• Coatings can be ground and/or lapped to very smooth finishes.</li> </ul>
		<b>C-408.25</b>	-45 +22 µm	
		<b>C-408.45</b>	-63 +15 µm	

<b>TUNGSTEN CARBIDE</b>				
<b>Powder Type</b>	<b>Nom.Composition</b>	<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>
WC-Ni 88/12	Ni 12.0% WC Bal.  Agglomerated & Sintered	K-611.17	-38 +10 µm	<ul style="list-style-type: none"> <li>• Plasma, HVOF</li> <li>• Hard, tough, dense coatings with good abrasion, erosion and sliding wear resistance.</li> <li>• Very fine as sprayed surfaces possible</li> <li>• Better corrosion resistance the WC-Co coatings</li> <li>• Useful up to 480°C (900°F)</li> <li>• Excellent low temperature wear properties</li> <li>• Diamond wet grinding.</li> </ul>
		K-611.23	-45 +15 µm	
WC-Ni 83/17	Ni 17.0% WC Bal.  Agglomerated & Sintered	K-612.17	-38 +10 µm	<ul style="list-style-type: none"> <li>• Plasma, HVOF</li> <li>• Hard, tough, dense coatings with good abrasion, erosion and sliding wear resistance.</li> <li>• 17% Ni Coatings have better toughness than 12% Ni coatings</li> <li>• Very fine as sprayed surfaces possible</li> <li>• Better corrosion resistance the WC-Co coatings</li> <li>• Useful up to 480°C (900°F)</li> <li>• Excellent low temperature wear properties</li> <li>• Diamond wet grinding.</li> </ul>
		K-612.23	-45 +15 µm	
WC-NiCr 85/10/5	Ni 10.0% Cr 5.0% WC Bal.  Agglomerated & Sintered	K-617.23	-45 +15 µm	<ul style="list-style-type: none"> <li>• Coatings made from K-617 protect against fretting, abrasion and hammer (impact) wear and sliding wear.</li> <li>• K-617 has been designed to produce coatings that are wear resistant in a seawater environment.</li> <li>• The use above 500 °C (930 °F) is not recommended.</li> <li>• As K-617 is cobalt-free, it can also be used in radioactive environments.</li> <li>• K-617 coatings have a higher hardness than tungsten carbide – nickel coatings as a consequence of the hardening effect of chromium in the binder alloy, but toughness is reduced.</li> <li>• The hardness of a K-617 coating is slightly lower than that of a tungsten carbide-cobalt-chromium coating.</li> </ul>

## Powders

TUNGSTEN CARBIDE				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
WC-Co 88/12	Co 12.0% W Bal.  Agglomerated & Sintered	K-624.15	-30 +5 µm	<ul style="list-style-type: none"> <li>• Plasma, HVOF</li> <li>• Medium WC</li> <li>• Hard, dense coatings with good abrasion, erosion and sliding wear resistance.</li> <li>• Low oxidation and corrosion resistance</li> <li>• Useful up to 480°C (900°F)</li> <li>• Excellent low temperature wear properties</li> <li>• Diamond wet grinding.</li> </ul>
		K-624.17	-38 +10 µm	
		K-624.23	-45 +15 µm	
		K-624.33	-53 +20 µm	
WC-Co 83/17	Co 17.0% WC Bal.  Agglomerated & Sintered	K-674.15	-30 +5 µm	<ul style="list-style-type: none"> <li>• HVOF</li> <li>• Course WC</li> <li>• Higher Co level then K-624 results is improved toughness, impact strength and ductility</li> <li>• Useful up to 480°C (900°F)</li> <li>• Low oxidation and corrosion resistance</li> <li>• Diamond wet grinding.</li> </ul>
		K-674.17	-38 +10 µm	
		K-674.23	-45 +15 µm	
WC-Co-Cr 86/10/4	Co 10.0% Cr 4.0% WC Bal.  Sintered & Crushed	K-646.17	-38 +10 µm	<ul style="list-style-type: none"> <li>• HVOF and APS</li> <li>• The CoCr matrix shows higher corrosion and abrasion resistance that the Co matrix materials</li> <li>• Usable in wet corrosive environments</li> <li>• Dense, smooth coatings with fine microstructure and high bond strengths</li> <li>• Used for Hard Chrome Replacement</li> <li>• Diamond wet grinding.</li> </ul>
		K-646.23	-45 +15 µm	
WC-Co-Cr 86/10/4	Co 10.0% Cr 4.0% WC Bal.  Agglomerated & Sintered	K-647.15	-30 +5 µm	<ul style="list-style-type: none"> <li>• HVOF</li> <li>• Medium WC</li> <li>• The CoCr matrix shows higher corrosion and abrasion resistance that the Co matrix materials</li> <li>• Usable in wet corrosive environments</li> <li>• Dense, smooth coatings with fine microstructure and high bond strengths</li> <li>• Used for Hard Chrome Replacement</li> <li>• Diamond wet grinding.</li> </ul>
		K-647.17	-38 +10 µm	
		K-647.23	-45 +15 µm	
		K-647.33	-53 +20 µm	

<b>TUNGSTEN CARBIDE</b>				
<b>Powder Type</b>	<b>Nom.Composition</b>	<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>
WC-Co-Cr 86/10/4	Co 10.0%	<b>K-648.15</b>	-30 +5 µm	<ul style="list-style-type: none"> <li>• HVOF</li> <li>• Fine WC</li> <li>• The CoCr matrix shows higher corrosion and abrasion resistance than the Co matrix materials</li> <li>• Usable in wet corrosive environments</li> <li>• Dense, smooth coatings with fine microstructure and high bond strengths</li> <li>• Used for Hard Chrome Replacement</li> <li>• Diamond wet grinding.</li> </ul>
	Cr 4.0%	<b>K-648.17</b>	-38 +10 µm	
	W Bal.	<b>K-648.23</b>	-45 +15 µm	
WC-Co-Cr 86/10/4	Co 10.0%	<b>K-649.15</b>	-30 +5 µm	<ul style="list-style-type: none"> <li>• HVOF</li> <li>• Sub-Micron WC</li> <li>• The CoCr matrix shows higher corrosion and abrasion resistance than the Co matrix materials</li> <li>• Usable in wet corrosive environments</li> <li>• Dense, smooth coatings with fine microstructure and high bond strengths</li> <li>• Used for Hard Chrome Replacement</li> <li>• Diamond wet grinding.</li> </ul>
	Cr 4.0%	<b>K-649.17</b>	-38 +10 µm	
	W Bal.	<b>K-649.23</b>	-45 +15 µm	
WC-CoCrNi 85/9/5/1	Co 9.0%	<b>K-665.17</b>	-38 +10 µm	<ul style="list-style-type: none"> <li>• HVOF</li> <li>• Medium WC</li> <li>• The CoCrNi matrix shows higher corrosion and abrasion resistance than the Co and CoCr matrix materials</li> <li>• Usable in wet corrosive environments</li> <li>• Dense, smooth coatings with fine microstructure and high bond strengths</li> <li>• Used for Hard Chrome Replacement</li> <li>• Diamond wet grinding.</li> </ul>
	Cr 5.0%	<b>K-665.23</b>	-45 +15 µm	
	Ni 1.0%			
	WC Bal.			

## Powders

TUNGSTEN CARBIDE				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
WC-CrC-Ni 73/20/7	Ni 7.0%	<b>K-607.15</b>	-30 +5 µm	<ul style="list-style-type: none"> <li>• HVOF</li> <li>• Fine WC</li> <li>• Useful up to 700°C</li> <li>• Higher corrosion, oxidation and chemical resistance than other WC based coatings</li> <li>• Smooth coating with fine micro structure</li> <li>• High bond strength</li> <li>• Diamond wet grinding.</li> </ul>
	CrC 20.0%	<b>K-607.17</b>	-38 +10 µm	
	W Bal.	<b>K-607.23</b>	-45 +15 µm	
	Agglomerated & Sintered	<b>K-607.33</b>	-53 +20 µm	

YTTRIUM OXIDE				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
Y <sub>2</sub> O <sub>3</sub>	Y <sub>2</sub> O <sub>3</sub> 99,5%	<b>C-200.45</b>	-65+15 µm	<ul style="list-style-type: none"> <li>• Stable at high temperatures</li> <li>• Plasma etch and erosion resistance on surfaces exposed to reactive plasma gases in semiconductor manufacturing systems, such as vacuum chamber walls and other components.</li> <li>• Used for protection of graphite sheets in the hard metal industry</li> <li>• Max. operating temperature in air 2200 °C (on graphite 1550 °)</li> </ul>
	Agglomerated and Sintered	<b>C-200.71</b>	-90+45 µm	

ZIRCONIUM OXIDE				
Powder Type	Nom.Composition	FST p/n	Size Range	Typical Properties and Applications
ZrO <sub>2</sub> -Y <sub>2</sub> O <sub>3</sub>	ZrO <sub>2</sub> Bal.	<b>C-295.45</b>	-63 +15 µm	<ul style="list-style-type: none"> <li>• Excellent thermal barrier properties</li> <li>• Stabilizes during spray process</li> <li>• Useful up to 1300°C (2450°F)</li> <li>• Very good thermal shock resistance</li> <li>• Thick, high porosity coating possible.</li> </ul>
	Y <sub>2</sub> O <sub>3</sub> 8.0%	<b>C-295.71</b>	-90 +15 µm	
	Spray Dried	<b>C-295.92</b>	-125 +45 µm	

<b>ZIRCONIUM OXIDE</b>				
<b>Powder Type</b>	<b>Nom.Composition</b>	<b>FST p/n</b>	<b>Size Range</b>	<b>Typical Properties and Applications</b>
ZrO <sub>2</sub> -Y <sub>2</sub> O <sub>3</sub>	ZrO <sub>2</sub> Bal. Y <sub>2</sub> O <sub>3</sub> 8.0%  Fused & Crushed	C-297.02	-22 +5 μm	<ul style="list-style-type: none"> <li>• Excellent thermal barrier properties</li> <li>• Stabilizes during spray process</li> <li>• Useful up to 1300°C (2450°F)</li> <li>• Very good thermal shock resistance.</li> <li>• Used for DVC (Dense Vertically Cracked) Coatings</li> </ul>
		C-297.23	-45 +15 μm	
ZrO <sub>2</sub> -22MgO	ZrO <sub>2</sub> Bal. MgO 24.0%  Fused & Crushed	C-234.25	-45 +22 μm	<ul style="list-style-type: none"> <li>• Good thermal barrier properties</li> <li>• Resistant to molten metals</li> <li>• Good particle erosion resistance</li> <li>• Useful up to 900°C .</li> </ul>
		C-234.71	-90 +45 μm	
ZrO <sub>2</sub> -5CaO	ZrO <sub>2</sub> Bal. CaO 5.0%  Fused & Crushed	C-241.25	-45 +22 μm	<ul style="list-style-type: none"> <li>• Thermal barrier coatings used in rocket and turbine engine combustion chambers and other hot section components.</li> <li>• Lining for special purpose crucibles to prevent contamination of the molten contents.</li> <li>• Abrasive wear resistant coatings for diesel engine pistons, valves, cylinder heads and coatings for casting molds and troughs up to approximately 900 °C. Coatings resist wetting and the corrosive effects of molten metal.</li> </ul>
		C-241.71	-90 +45 μm	